


JC02 Rec'd PCT/PTO 27 MAR 2002

FORM PTO-1390 OFFICE (REV. 10-95)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK		ATTORNEY'S DOCKET NUMBER	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				CM2199M2 U.S. APPLICATION NO. (if known, see 37 CFR 1.5) 10/089340	
INTERNATIONAL APPLICATION NO. PCT/US00/26975		INTERNATIONAL FILING DATE 29 September 2000		PRIORITY DATE CLAIMED 01 October 1999	
TITLE OF INVENTION Reactive Dye Compounds					
APPLICANT(S) FOR DO/EO/US UNDERINER, Todd Laurence et al.					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information.					
<p>1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.</p> <p>2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.</p> <p>3. <input type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(l).</p> <p>4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</p> <p>5. <input checked="" type="checkbox"/> A copy of the International Application was filed (35 U.S.C. 371(c)(2))</p> <p style="margin-left: 20px;">a. <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 20px;">b. <input type="checkbox"/> has been transmitted by the International Bureau.</p> <p style="margin-left: 20px;">c. <input checked="" type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US).</p> <p>6. <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</p> <p>7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))</p> <p style="margin-left: 20px;">a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 20px;">b. <input type="checkbox"/> have been transmitted by the International Bureau.</p> <p style="margin-left: 20px;">c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</p> <p style="margin-left: 20px;">d. <input checked="" type="checkbox"/> have not been made and will not be made.</p> <p>8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</p> <p>10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).</p> <p>Items 11. to 16. below concern document(s) or information included:</p> <p>11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</p> <p>12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</p> <p>13. <input checked="" type="checkbox"/> A FIRST preliminary amendment.</p> <p style="margin-left: 20px;"><input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.</p> <p>14. <input type="checkbox"/> A substitute specification.</p> <p>15. <input checked="" type="checkbox"/> A change of power of attorney and/or address letter.</p> <p>16. <input type="checkbox"/> Other items or information:</p>					
<p>"Express Mail" mailing label number EL48362152275</p> <p>Date of Deposit 27 March 2002</p> <p>I hereby certify that this paper/fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to The Assistant Commissioner of Patents, Washington, D.C. 20231.</p> <p>Assistant Mailing Application.</p> <p>Signature <i>Original [Signature]</i></p>					

U.S. APPLICATION NO. (if known, see 37 CFR 1.5) 10/089340		INTERNATIONAL APPLICATION NO. PCT/US00/26975		ATTORNEY'S DOCKET NUMBER CM2199M2	
				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$740	
Surcharge of \$130.00 for furnishing the oath or declaration later than 20 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$0	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	30-20 =	10	x \$18.00	180	
Independent Claims	4-3 =	1	x \$84.00	84	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			\$280.00	\$0	
TOTAL OF ABOVE CALCULATIONS =				\$1004	
Processing fee of \$130.00 for furnishing the English translation later than 20 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$0	
TOTAL NATIONAL FEE =				\$1004	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28,3.31). \$40.00 per property +				\$0	
TOTAL FEES ENCLOSED =				\$1004	
				Amount to be refunded	\$
				charged	\$
<p>a. <input type="checkbox"/> A check in the amount of \$ ____ to cover the above fees is enclosed.</p> <p>b. <input checked="" type="checkbox"/> Please charge my Deposit Account No. <u>16-2480</u> in the amount of \$ <u>1004</u> to cover the above fees. A duplicate copy of this sheet is enclosed.</p> <p>c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>16-2480</u>. A duplicate copy of this sheet is enclosed.</p> <p>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</p> <p>SEND ALL CORRESPONDENCE TO:</p>					
B. J. Corstanje, Patent Attorney Customer Number 27752				 Signature T. David Reed Name 32,931 Registration Number	

CM2199M2

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In the U.S. National Phase Entry
Under 35 USC 371 from
International Application of
BROADBENT, Peter Jeffrey et al.
Int'l. Application No. PCT/US00/26975
Filed in the RO/US on 29 September 2000
Entitled: *Reactive Dye Compounds*

PRELIMINARY AMENDMENT UNDER 37 CFR §1.112

Assistance Commissioner for Patents
Box PCT
Washington, D. C. 20231

Dear Sir:

Prior to Examination and computation of the fees for entering the captioned International Application into the U. S. National Phase, please preliminarily amend the above-identified application as follows and consider the following Remarks.

AMENDMENTS

IN THE CLAIMS

3. A reactive dye compound according to Claim 1 wherein Y is derived from the hydrated form of a reducing sugar selected from an aldose or a ketose, or the hydrated form of formic acid.
7. A reactive dye compound according to Claim 1 wherein Y is derived from glucose, sucrose or fructose or the hydrated form of formic acid.
9. A reactive dye compound according to Claim 1 wherein Y is -O-(CHOH)₄(CHOHCH₂OH).
12. A reactive dye compound according to Claim 10 wherein r is 0.

15. Use of a compound according to Claim 1 for dyeing cellulosic substrates.
16. Use of a compound according to Claim 1 for dyeing wool.
17. Use of a compound according to Claim 1 for dyeing polyamide substrates, preferably nylon.
18. Use of a compound according to Claim 1 for dyeing silk.
19. Use of a compound according to Claim 1 for dyeing keratin.
20. Use of a compound according to Claim 1 for dyeing leather.
21. Process for the preparation of a compound according to Claim 1 comprising the steps of reacting a first starting material with a second starting material, the first starting material comprising at least one chromophore and at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore group either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group, the second starting material being a compound containing a suitable Y group.
23. Process according to Claim 21 wherein the process is carried out at a pH of from about 2 to about 8.
24. Process according to Claim 21 wherein the second starting material is added to the first starting material slowly.
25. Product obtainable by the process according to Claim 21.
26. A dye composition comprising the compound of Claim 1 or the product of Claim 21.


30. A dye composition according to Claim 26 wherein the pH of the composition is in the range of from about 2 to about 5, when an acidic buffer is present, and in the range of from about 4 to about 8 when a neutral buffer is present.

REMARKS

Claims 1, 2, 4-6, 8, 10, 11, 13, 14, 22, 27, 28 and 29 remain in this application. Claims 3, 7, 9, 12, 15-21, 23-26 and 30 have been amended by eliminating multiple dependencies and deleting preferably claims. Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "Version With Markings to Show Changes Made."

The support for these amendments is found in the claims as originally filed. These amendments are being entered to bring the claims into conformance with, *inter alia*, 37 CFR §1.75, no new matter is added.

Respectfully submitted for Applicants,

By 
T. David Reed
Agent for Applicant
Registration No. 32,931

Cincinnati, Ohio
20 March 2002
(513)627-7025/FAX (513)627-6333

“VERSION WITH MARKINGS TO SHOW CHANGES MADE”

Claims:

1. A reactive dye compound comprising:

- (a) at least one chromophore moiety;
- (b) at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore moiety either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group L;

characterised in that at least one $\text{SO}_2\text{C}_2\text{H}_4$ group is substituted on its terminal carbon atom with at least one Y group wherein Y is derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the $\text{SO}_2\text{C}_2\text{H}_4$ group thereby forming a hemiacetal.

2. A reactive dye compound according to Claim 1 wherein Y is derived from a hydrated aldehyde or ketone or the hydrated form of formic acid.

3. A reactive dye compound according to Claim 1 or 2 wherein Y is derived from the hydrated form of a reducing sugar selected from an aldose or a ketose, or the hydrated form of formic acid.

4. A reactive dye compound according to Claim 3 wherein said aldose is selected from an aldotriose, an aldotetrose, an aldopentose, an aldohexose, an aldohexose, and an aldooctose, and mixtures thereof.

5. A reactive dye compound according to Claim 4 wherein said aldose is an aldopentose selected from ribose, xylose, arabinose, deoxyribose and fructose, and mixtures thereof.


6. A reactive dye compound according to Claim 5 wherein said aldose is an aldohexose selected from glucose, galactose, talose, mannose, altrose, allose and rhamnose, and mixtures thereof.

7. A reactive dye compound according to ^{CLAIM 1} [any of Claims 1 to 6] wherein Y is derived from glucose, sucrose or fructose or the hydrated form of formic acid.

8. A reactive dye compound according to Claim 3 wherein said ketose is selected from an aldotetralose, an aldopentulose, an aldohexulose, an aldoheptulose, and an aldooctulose, and mixtures thereof.

9. A reactive dye compound according to ^{CLAIM 1} [any of Claims 1 to 8] wherein Y is -O-(CHOH)₄(CHOHCH₂OH).

10. A reactive dye compound having the formula (I):




wherein: D is a chromophore group;

r is 0 or 1

L is a linking group selected from:

NH, $(CH_2)_n$, $N-(CH_2)_nN$, $-(CH_2)_n-N$, NR (R is C1-C4 alkyl)



wherein Ar is an aryl group, preferably benzene, Y is as defined above, X is selected from thio-derivatives, halogen (preferably fluorine and chlorine), amines, alkoxy groups, carboxylic acid groups, CN, N₃, quaternized nitrogen derivatives, Q⁺, and oxy- or thio- carbonyl


derivatives having the formula $-A(\text{CO})\text{R}^*$ wherein A is selected from O or S, where R^* is an organic residue which contains at least one nucleophilic group, wherein the nucleophilic group is preferably selected from OH, NH_2 , SH, COOH, $-\text{N}=\text{}$, NHR^1 and NR^1R^2 wherein R^1 and R^2 may be the same or different and may be selected from C_1 - C_4 alkyl; Z is a nitrogen-containing heterocycle, n is an integer of from 1 to 4;

and salts thereof.

11. A reactive dye compound according to Claim 10 wherein Z is selected from triazine, pyrimidine, quinoxaline, pyrimidinone, phthalazine, pyridazone and pyrazine.


12. A reactive dye compound according to Claim 10 [or 11] wherein r is 0.

13. A reactive dye compound having the structure:



wherein D, Z, and Y are as defined above.

14. A reactive dye compound having the structure:



wherein D, Y and Ar are as defined above.

15. Use of a compound according to [CLAIM 1] any of Claims 1 to 14 for dyeing cellulosic substrates [preferably cotton].

16. Use of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] for dyeing wool.
17. Use of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] for dyeing polyamide substrates, preferably nylon.
18. Use of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] for dyeing silk.
19. Use of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] for dyeing keratin [preferably hair].
20. Use of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] for dyeing leather.
21. Process for the preparation of a compound according to ^{CLAIM 1} [any of Claims 1 to 14] comprising the steps of reacting a first starting material with a second starting material, the first starting material comprising at least one chromophore and at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore group either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group, the second starting material being a compound containing a suitable Y group [preferably the hydrated form of a reducing sugar].
22. Process according to Claim 21 wherein the reducing sugar is selected from sucrose, glucose and mixtures thereof.
23. Process according to Claim 21 [or 22] wherein the process is carried out at a pH of from about 2 to about 8.
24. Process according to ^{CLAIM 21} [any of Claims 21 to 23] wherein the second starting material is added to the first starting material slowly [preferably dropwise, preferably over several hours, preferably 1 to 5 hours, more preferably 1 to 3 hours].
25. Product obtainable by the process according to ^{CLAIM 21} [any of Claims 21 to 24].

26. A dye composition comprising the compound of ^{CLAIM 1} any of Claims 1 to 14 or the product of any of Claims 21 to 25 ^{CLAIM 21}.
27. A dye composition according to Claim 26 wherein the composition is in the form of a solid mixture and further comprises an acidic or neutral buffer.
28. A dye composition according to Claim 26 wherein the composition is in the form of a liquid and further comprises water and an acidic or neutral buffer.
29. A dye composition according to Claim 26 wherein the composition is in the form of a paste and further comprises water, thickening agent and an acidic or neutral buffer.
30. A dye composition according to ^{CLAIM 26} any of Claims 26, 28 or 29 wherein the pH of the composition is in the range of from about 2 to about 5 [preferably from about 2 to about 3] when an acidic buffer is present, and in the range of from about 4 to about 8 [preferably from about 6 to about 8] when a neutral buffer is present.

Rec'd PCT/PTO 27 MAR 2002

Reactive Dye CompoundsTechnical Field

The present invention relates to reactive dye compounds. In particular the present invention relates to reactive dye compounds having improved dye-bath Exhaustion (E) and improved dye-fibre covalent Fixation (F).

Background of the Invention

Reactive dye compounds are known in the art for dyeing various substrates. Such substrates include for example proteinaceous materials such as keratin, e.g. found in hair, skin and nails and various animal body parts such as horns, hooves and feathers, and other naturally occurring protein containing materials, e.g. silk and saccharide-derived materials such as those derived from cellulose or cellulose derivatives, e.g. natural products such as cotton, and synthetic fibres such as polyamides.

Examples of classes of such reactive dyes which are well known in the art include dyes containing a vinyl sulphone group or vinyl sulphone precursor groups such as those commercially available from Dystar under the tradename Remazol.

There are many different types of commercially-available reactive dyes for dyeing cellulosic and polyamide-type substrates. However, a critical problem still facing the textile dye industry today is the significant level of dyestuff material which remains in the effluent waste water after the dyeing process is finished. The industry measure for this problem is known as dye-bath Exhaustion (E). A high Exhaustion value for a particular dye compound means that a low level of spent dye remains in the effluent after the dyeing process is complete, while a low Exhaustion value means that a high level of spent dye remains in the effluent. There is clearly a need therefore for new dye compounds which have higher Exhaustion Values compared with commercially available dye compounds, and which provide benefits in terms of reducing levels of spent dyestuff in effluent water.

As well as having a high Exhaustion Value, it is also important for a dye compound to have a high dye-fibre covalent Fixation Value (F). The Fixation Value (F) of a reactive dye compound is a measure of the extent of covalent bonding with the substrate based on the dye originally absorbed during the dyeing process. Thus 100% Fixation means that 100% of the absorbed dye covalently bonds to the substrate. Thus, there is clearly a need to provide dye compounds having increased Fixation Values. A high Fixation Value can result in a simplification of the post dyeing "soaping off process" traditionally associated with fiber reactive dye compounds. In particular, a high Fixation Value can result in a reduced time spent on the "soaping off process" together with a reduced cost.

It has now been surprisingly found that a new class of fibre reactive dye compounds derived from vinyl sulphone dyes and their precursors such as chloroethylsulphone, sulphatoethylsulphone, phosphoethylsulphone, and other blocked ethyl sulphones as known in the art, comprising at least one chromophore group, at least one $\text{SO}_2\text{C}_2\text{H}_4$ group and at least one substituent derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxyketone or the hydrated form of formic acid, linked via one of its oxygen atoms to the terminal carbon atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group and hence forming a hemiacetal, such as for example the hydrated form of sucrose or glucose, and the hydrated form of formic acid, exhibit significantly increased values of Exhaustion (E) and Fixation (F). These dyes can be used on a wide variety of substrates. They are particularly useful for cellulosic substrates, such as cotton and/or cotton blends, and show significant improvements in terms of decreasing the amount of spent dyestuff in effluent, increasing dye affinity to the substrate, increasing the efficiency of the dye-substrate covalent reaction, and simplifying the post dyeing "soaping off process" traditionally associated with reactive dyes. In addition, the compounds of the present invention provide significantly more intense dyeings not achievable with current reactive dyes, and can be used for both high and low temperature dyeing, hence reducing the cost of the dyeing process. Furthermore, the compounds of the present invention can be used together with specific chromophores for cellulose substrate dyeing leading to significantly reduced levels of salt needed for dyeing.

Summary of the Invention

According to the present invention there is provided a reactive dye compound comprising:

- (a) at least one chromophoric moiety
- (b) at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophoric moiety either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group L;

characterised in that at least one $\text{SO}_2\text{C}_2\text{H}_4$ group is substituted on its terminal carbon atom with at least one Y group wherein Y is derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the $\text{SO}_2\text{C}_2\text{H}_4$ group thereby forming a hemiacetal.

The compounds of the present invention exhibit increased Exhaustion (E), Fixation (F) and Efficiency (T) values and provide improvements in terms of reducing spent dyestuff in effluent, increasing dye affinity to the substrate, increasing the efficiency of the dye-substrate covalent reaction, ability to carry out the long-liquor dyeing process at room temperature as well as at elevated temperatures, and simplifying the post dyeing "soaping off process" traditionally associated with fiber reactive dyes. In addition, the compounds of the present invention provide significantly more intense dyeings, i.e. greater colour intensity in the dyed substrate, without compromising levelness. Typical Exhaustion Values for the compounds and products herein are greater than 95%. Typical Fixation Values for the compounds and products herein are greater than 95%.

Detailed Description of the Invention

As used herein the term "reactive dye" means a dye containing one or more reactive groups, capable of forming covalent bonds with the substrate to be dyed, or a dye which forms such a reactive group in situ.

As used herein the term "Exhaustion" in relation to reactive dyes means the percentage of dye which is transferred from a solution of the dye to the substrate to be treated at the end

of the dyeing process, before rinsing and soaping. Thus 100% Exhaustion means that 100% of the dye is transferred from the dye solution to the substrate.

As used herein the term "Fixation" in relation to reactive dyes means the percentage of dye which covalently bonds with the substrate, based on the dye originally absorbed during the dyeing process. Thus 100% Fixation means that 100% of the dye absorbed is covalently bonded with the substrate.

The total efficiency of reactive dyes can be measured by their Efficiency Value (T) which can be calculated from the Exhaustion Value (E) and Fixation Value (F) using the following equation:

$$\%T = (F \times E) / 100$$

The compounds of the present invention comprise a chromophoric moiety, at least one $\text{SO}_2\text{C}_2\text{H}_4$ group linked to the chromophore group either directly via the sulphur atom or via a linking group L and at least one Y substituent wherein the Y substituent is derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the $\text{SO}_2\text{C}_2\text{H}_4$ group thereby forming a hemiacetal.

Chromophoric Moiety

The reactive dye compounds herein can comprise one or more chromophoric moieties (D). In reactive dye compounds comprising two or more chromophoric moieties these can be the same or different. Preferably the reactive dye compounds herein comprise from one to three chromophoric moieties, preferably one or two chromophoric moieties, preferably one.

Any chromophoric moieties suitable for use for dyeing substrates can be used in the present invention. The term chromophore as used herein means any photoactive compound and includes any coloured or non-coloured light absorbing species, eg. fluorescent brighteners, UV absorbers, IR absorbing dyes.

Suitable chromophoric moieties for use in the dye compounds herein include the radicals of monoazo, disazo or polyazo dyes or of heavy metal complex azo dyes derived therefrom or of an anthraquinone, phthalocyanine, formazan, azomethine, dioxazine, phenazine, stilbene, triphenylmethane, xanthene, thioxanthene, nitroaryl, naphthoquinone, pyrenequinone or perylenetetracarboximide dye.

Suitable chromophoric moieties for use in the dye compounds herein include those disclosed in EP-A-0,735,107 (Ciba-Geigy), incorporated herein by reference, including the radicals described therein which contain substituents customary for organic dyes, such as sulphonate substituents which enhance the water solubility of the dye compound.

Most preferred chromophoric D groups for use herein are polysulphonated azo chromophores such as those present in Procion (RTM) dyes commercially available from BASF, Drimalan (RTM) dyes commercially available from Clariant, Drimarene (RTM) dyes commercially available from Clariant and Levafix (RTM), Remazol (RTM) dyes commercially available from Dystar and Sumifix supra (RTM) dyes commercially available from Sumitomo.

Substituent Y

At least one of the $\text{SO}_2\text{C}_2\text{H}_4$ groups is substituted on the terminal carbon atom with at least one Y group wherein Y is a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the $\text{SO}_2\text{C}_2\text{H}_4$ group thereby forming a hemiacetal.


Particularly preferred Y groups herein are derived from the hydrated forms of an aldehyde or ketone. Preferably the Y group is derived from the hydrated form of a reducing sugar selected from an aldose or a ketose.

Suitable aldose materials for use herein include an aldotriose, an aldotetrose, an aldopentose, an aldohexose, an aldohexose, an aldohexose, an aldohexose, and mixtures thereof. A preferred aldose material for use herein is an aldopentose material, preferably selected from ribose, xylose, arabinose, deoxyribose and fructose and mixtures thereof. Another preferred aldose material for use herein is an aldohexose material, preferably selected from glucose, galactose, talose, mannose, altrose, allose and rhamnose, and mixtures

thereof. Most preferred for use herein are the hydrated forms of glucose, sucrose and fructose. Isomers of the hydrated forms of sucrose or glucose can be formed by acid hydrolysis of sucrose and glucose, respectively. A preferred Y group herein is a group derived from the hydrated form of sucrose or glucose, namely -O-(CHOH)₄(CHOHCH₂OH).

Suitable ketose materials for use herein include an aldotetrol, an aldopentulose, an aldoheptulose, an aldooctulose and mixtures thereof.

Other suitable aldehyde and ketone materials which can be converted to their hydrated form via acid hydrolysis include, but are not limited to, furfural, glucosamine, l-glycine aldehyde, l-mannose, l-galactose, piperidone, 2-methylene-3-quinuclidinone dihydrate HCl, ascorbic acid, paraformaldehyde, glyoxylic acid, glyoxal, glutaraldehyde, chloral, dihydroxy tartaric acid, 2-2-dihydroxy-5-methoxy-1,5-methoxy-3-indandione hydrate (ninhydrin), 2-2-dihydroxy-1H-benz(F)indene-1,3(2H)-dione hydrate, mesoxalic acid, alloxan, pyruvic acid, glyceraldehyde, 2,5-piperazine-dione, d-erythrose, d-threose, d-ribose, d-arabinose, d-xylose, d-lyxose, d-ribulose, and the compound having the structure:




Particularly preferred Y groups herein are groups derived from saccharide molecules such as sucrose and glucose, and the like, which have been hydrolysed to their hydrated forms. A preferred Y group herein is a group derived from the hydrated isomer of sucrose or glucose, namely -O-(CHOH)₄(CHOHCH₂OH). Hydrated isomers of sucrose and glucose can be formed by acid hydrolysis of sucrose and glucose, respectively. When saccharides such as sucrose and glucose are subjected to acid hydrolysis they can also

form a polymeric structure and hence in that case the Y group would also be polymeric.

Another preferred Y group is derived from the hydrated form of formic acid, (eg. -CH(OH)(OH)), which can also be polymeric.

Another preferred Y group is derived from the hydrated form of formic acid (eg. -CH(OH)(OH))

Preferred reactive dye compounds of the present invention may be represented by the following formulae (I)










wherein: D is a chromophore group;

r is 0 or 1, preferably 0,

L is a linking group selected from

NH, (CH₂)_n, N-(CH₂)_nN, -(CH₂)_n-N, NR (R is C1-C4 alkyl)






wherein Ar is an aryl group, preferably benzene, Y is as defined above, X is selected from thio-derivatives, halogen (preferably fluorine and chlorine), amines, alkoxy groups, carboxylic acid groups, CN, N₃, quaternized nitrogen derivatives, Q⁺, and oxy- or thio- carbonyl derivatives having the formula -A(CO)R* wherein A is selected from O or S, where R* is an organic residue which contains at least one nucleophilic group, wherein the nucleophilic group is preferably selected from OH, NH₂, SH, COOH, -N=, NHR¹ and NR¹R² wherein R¹ and R² may be the same or different and may be selected from C₁-C₄ alkyl; Z is a nitrogen-containing heterocycle, n is an integer of from 1 to 4;

and salts thereof.


When the starting dye compound has multiple reactive groups, for example two reactive groups, one can substitute, for example, one or both of these reactive groups by one or two Y groups, wherein two Y groups in the same molecule may be the same or different.

Particularly preferred reactive dye compounds herein have the structure I(a) below:



wherein D, L, and r are as defined above.


An especially preferred reactive dye compound herein has the following structure (Ib)



wherein D is as defined above.


Compounds having the structure Ib above can be obtained by using a vinyl sulphone dye as the starting dye, such as for example, Remazol Red RB, Remazol Yellow 3RS, Remazol Turquoise Blue G, and reacting it with a compound containing a Y group such as for example the hydrated forms of sucrose, glucose and formic acid.

Another preferred reactive dye compound herein has the structure (Ic) below:



wherein D, Y are as defined above and Z is a nitrogen-containing heterocycle as defined below. Examples of compounds having the structure (Ic) above can be obtained by using as the starting dye, a dye containing both vinyl sulphone and nitrogen-containing heterocycle functional groups, such as for example, Cibacron Red C2G, Cibacron Yellow C2R and Cibacron Blue CR. These starting dyes are reacted with compounds containing a suitable Y group, such as for example, the hydrated form of glucose, sucrose or formic acid.

Yet another preferred reactive dye compound herein has the structure (Id) below:



wherein D, Ar, and Y are as defined above and Z is a nitrogen-containing heterocycle as defined below. Examples of compounds having the structure (Id) above can be obtained by using as the starting dye, a dye containing both vinyl sulphone and nitrogen-containing heterocycle functional groups, and an additional benzene group as part of the L linking group, such as for example, Sumifix Supra Red 2BF and Sumifix Supra Yellow 3RF. These starting dyes are reacted with compounds containing a suitable Y group, such as for example, the hydrated form of glucose, sucrose or formic acid.

The Y group may also exist in a polymeric form due to a polymer being formed when the reducing sugar or formic acid is hydrolysed with acid.

Nitrogen-containing Heterocycle (Z)

Suitable nitrogen containing heterocycles for use herein include monocyclic, bicyclic or polycyclic, unsaturated heterocycles containing at least one nitrogen heteroatom. When monocyclic rings are used, they are preferably selected from unsaturated rings having from about 3 to about 7 ring atoms, especially 5 or 6 ring atoms, comprising from about 1 to about 3 nitrogen heteroatoms, preferably 2 or 3 nitrogen heteroatoms. When bicyclic heterocycles are used, they preferably comprise an unsaturated nitrogen containing heterocycle having 3 to 7 ring atoms, preferably an unsaturated nitrogen containing heterocycle having 5 or 6 ring atoms comprising 1 or 2 nitrogen atoms, fused to a 5 to 7 membered carbocycle preferably a 6-membered unsaturated carbocycle. When bicyclic heterocycles are used, the oxy carbonyl substituents are preferably attached to the nitrogen containing heterocyclic ring.

Preferred for use herein are 5 or 6 membered unsaturated nitrogen containing monocyclic heterocyclic rings comprising 2 or 3 nitrogen heteroatoms or bicyclic rings containing a 5 or 6 membered unsaturated heterocyclic ring containing 2 nitrogen heteroatoms fused to a 6 membered unsaturated carbocycle.

Examples of suitable heterocycles for use herein include, but are not necessarily limited to triazine, pyrimidine, quinoxaline, pyrimidinone, phthalazine, pyridazone and pyrazine.

Preferred for use in the compounds herein are triazine, pyrimidine and quinoxaline.


The present invention further relates to processes for the preparation of dyes herein. In general, dyes herein are prepared by a process which comprises the steps of reacting a first starting material (preferably one mole) with a second starting material (preferably one mole), the first starting material comprising at least one chromophore, at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore group either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group (for example a Remazol dye), the second starting material being a compound containing a suitable Y group, such as for example the hydrated form of a saccharide material such as sucrose or glucose, or the hydrated form of formic acid. As described above, the hydrated form of the saccharide material is preferably obtained via acid hydrolysis. However there are other ways to obtain the hydrated form, for example, those hydrated aldehydes or ketones which are naturally occurring, e.g. 4-piperidone hydrate. It is preferable that the reaction is carried out at a pH of between 2 to 8, preferably 3 to 5 and over several hours, preferably 1 to 5 hours, more preferably 2-3 hours.

Compounds herein having the formula (I) are preferably prepared by reacting a first starting material (preferably one mole) with a second starting material (preferably one mole), the first starting material containing a $\text{D-(L)}_r\text{-SO}_2\text{-CH}_2\text{CH}_2\text{-}$ group as defined above (for example a Remazol dye, such as Remazol Brill Blue RS commercially available from Dystar), the second starting material being compound containing a Y group such as the hydrated form of a saccharide molecule such as sucrose and glucose. It is preferable that the reaction is carried out over several hours (2-5 hours). It is also important to add the saccharide dropwise over several hours, preferably from about 1 to about 5 hours, preferably from about 1 to about 3 hours.


The person skilled in the art will appreciate that there are other processes which may be used for manufacturing the compounds and products according to the present invention. Alternative preparation processes include, but are not limited to:

- (i) Diazotising the in situ formed sulphate ester of the hydroxy ethyl sulphone and then coupling this onto a suitable coupling component as in the following reactions:


Reaction 1:





Reaction 2:



Reaction 3:








(hydroxyethyl sulphone- para or meta base)



diazotisation followed by reaction with an aromatic precursor


Reaction 4:




diazotisation followed by reaction with an aromatic precursor

(ii) Reacting a vinyl sulphone or the sulphato ester with an active halogen in a preformed derivative of the chromophore as with the Sumifix Supra type of the Cicacron C type, or the acid chloride in copper phthalocyanine based turquoises, e.g. Reactive Blue 21, as in the following reactions:

Reaction 1:



Reaction 2:




monofunctional reactive dye

In all of these reactions it is possible to choose at what stage of the process to introduce the Y group.


(iii) In the case of blues based on the anthraquinone chromophore such as Reactive Blue 19, the condensation with Bromamine Acid is carried out using the metabase and then the intermediate dye is sulphated as a last step, e.g. by treatment with strong sulphuric acid or alternatively with sulphamic acid and an organic base, as in the following reactions:

Reaction 1:

18



Reaction 2:



Depending upon the reaction conditions (for example, amounts of each starting material, form of each starting material), mixtures of different dye compounds may be obtained in the final product, such mixtures containing for example, products formed from further substitution reactions, structural isomers and the like.

Hence according to another aspect of the present invention there is provided the product obtainable by any of the processes detailed herein.

In particular, there is provided a product obtainable by a process wherein the process comprises the steps of reacting a first starting material (preferably one mole) with a

second starting material (preferably one mole), the first starting material comprising at least one chromophore, at least one $\text{SO}_2\text{C}_2\text{H}_4$ which is attached to the chromophore group either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group L (for example a Remazol dye), the second starting material being a compound containing a suitable Y group, such as for example, the hydrated form of a saccharide material, preferably sucrose or glucose. It is preferable that the reaction is carried out at a pH of between 2 to 8, preferably 3 to 5 and over several hours, preferably 1 to 5 hours, more preferably 2-3 hours.

It is also preferable that the saccharide material is converted to its hydrated form before being reacted with the first starting material. This is preferably done by acid hydrolysis of the saccharide material.

The dye compounds herein are suitable for dyeing and printing a wide variety of substrates, such as silk, leather, wool, polyamide fibers and polyurethanes, keratin fibres such as hair, and in particular cellulosic materials, such as the natural cellulose fibres, cotton, linen, hemp and the like, paper, and also cellulose itself and regenerated cellulose, and hydroxyl-containing fibres contained in blend fabrics, for example blends of cotton with polyester or polyamide fibres.

The dye compounds of the present invention can be applied and fixed to the substrate in various ways, in particular in the form of a solid mixture, aqueous dye solutions and printing pastes. Thus according to the present invention there is provided a dye composition comprising one or more of the dye compounds described herein together with any carrier material suitable for use in a dye composition.

Preferred dye compositions herein comprise an acidic or neutral buffer material. Any acidic buffer suitable for use in dye compositions can be used herein. An example of a suitable buffer is a mixed phosphate buffer.

When the dye composition herein is in the form of a paste a preferred ingredient is a thickening agent. Any suitable thickening agents suitable for use in reactive dye compositions can be used herein.

When the dye composition is in the form of an aqueous solution or aqueous gel/paste, the dye composition preferably has a pH of from about 2 to about 8. When acidic buffers are used the dye composition preferably has a pH of from about 2 to about 5, especially from about 2 to about 3. When neutral buffers are used, the dye composition preferably has a pH of from about 4 to about 8, preferably from about 6 to about 8.

The dyeing and printing processes which can be used with the dyes herein are conventional processes which are well known and which have been widely described in the technical and patent literature. The dye compounds herein are suitable for dyeing both by the exhaust method (long liquor) and also by the pad-dyeing method, whereby the goods are impregnated with aqueous, salt-containing or salt-free dye solutions and the dye is fixed after an alkali treatment or in the presence of alkali, if appropriate with the application of heat. The dye compounds herein are also suitable for the cold pad-batch method, after which the dye together with the alkali is applied using a pad-mangle, the fabric batched on a roll. A dye-fibre covalent reaction occurs over several hours of storage at room temperature. Alternatively, padded or printed goods may be fixed by a steaming process using steam temperatures between 100-130°C. After fixing, the dyeings or prints are thoroughly rinsed with cold and hot water, if appropriate with the addition of an agent acting as a dispersant and promoting the diffusion of the non-fixed portions.

For cotton blends, a preferred dyeing process is as follows. A mixture of dyes is prepared comprising dyes according to the present invention together with direct dyes. The reactive dyes are fixed at a temperature of 100°C and the direct dyes are fixed at a temperature of 130°C. Uniform dyeing of the cotton blend is obtained.

Thus in accordance with another aspect of the present invention there is provided a use of the reactive dyes of the present invention for dyeing and printing substrates such as cotton, wool, nylon, silk, keratin, hair, leather, paper and the like. The compounds herein can be used in methods of dyeing all of the substrates listed above by applying an aqueous solution of one or more of the reactive dyes of the present invention to the substrate to be dyed under suitable conditions of pH and temperature.


The following examples serve to illustrate the compounds and compositions of the present invention.


The starting compounds and components given in the examples below can be used in the form of the free acid or in the form of their salts. As discussed above, the products obtained in the examples below may comprise mixtures of different dye compounds. In the Examples below all the starting materials are commercially available. In particular the Remazol dyes are available from Dystar Textilfarben, GmbH & Co., Deutschland KG, BU -R/F & E, Werk Hoechst, Building G834, D-65926 Frankfurt am Main, Germany, and the Sumifix dyes are available from Sumitomo Chemical Co. Ltd., 3-1-98, Kasugadenaka, Konohana-ku, Osaka 554, Japan. The Cibacron dyes are available from Ciba, Basle.

Examples

The reactive dye compounds of the present examples are prepared as follows. *X*g of pure Starting Dye is dissolved in 150ml of distilled water in a 400ml flask. The temperature of the reaction system is adjusted and maintained at *y*°C. The pH of the starting dye solution is adjusted to *z* using solid sodium carbonate. *A*g of sugar is dissolved in 50ml of distilled water. The pH of this sugar solution is adjusted to *b* and the sugar acid hydrolysis continues at ambient temperature for 30-35 minutes as shown below.

23

*Acid Hydrolysis of Glucose*




Acid Hydrolysis of Sucrose

The hydrolysed sugar solution is slowly added into the solution of starting dye. The rate of addition is such that the addition takes around c hours to complete. During the process of addition the temperature of the reaction system is maintained at $d^\circ\text{C}$. After addition of the sugar solution is complete, the reaction is allowed to continue for e hours. The endpoint of the reaction is indicated by the pH of the reaction system remaining constant for more than 5 minutes. At this point the final dye is obtained. Using 6N HCl, the pH of the system is then reduced to below 2.5 to terminate the reaction. KSCN (about 25% of

the total solution) is then added to the reaction mixture in order to precipitate the dye product. Filtration using Whatman filter paper is then carried out. The precipitate is then washed with acetone for 5-6 times (about 50ml of acetone used each time) to obtain the final dye product in fine powder form of *f* colour. Table I displays Examples 1 to 16 together with reaction conditions *y, z, b, c, d* and *e*, amounts of material *x* and *a*, colour of final product *f*, Starting Dye, Final Dye and type of sugar.


A possible synthetic mechanism for the reaction of the Cibacron dyes with glucose in its hydrated form is as follows:



where *R* = halogen, preferably Cl

It is also possible to carry out further reactions to obtain a bis-structure.

A possible synthetic mechanism for the reaction of the Sumifix dyes with glucose in its hydrated form is as follows:



If an excess of starting dye is used it is possible to get bis-structures in the final product.

The compounds prepared according to Examples 1 to 16 and at standard depths all have high Exhaustion Values, high Fixation Values, particularly on cellulosic substrates such as cotton, and show significant improvements in terms of reducing spent dyestuff in effluent, increasing dye affinity to the substrate, increasing the dye-substrate covalent

bonding, increasing the ability to dye substrates at room temperature, decreasing the amount of dye that is removed during the post dyeing "soaping off process" and therefore simplifying the post dyeing "soaping off process" traditionally associated with dyeing cotton with fibre reactive dyes and reduction of staining of adjacent white fabrics. In addition, the compounds prepared above provide more intense dyeings and require less levels of salt for dyeing cotton substrates. These advantages can be demonstrated by the following Examples 17 and 18.

Example 17

All dye compounds prepared according to Examples 1 to 16 can be used to dye cotton using the dyeing procedures detailed below. After the cotton dyeing procedure has been carried out a soaping-off process can also be carried out on the cotton fibre.

Cotton dyeing procedure

An aqueous dye solution is prepared containing a dye compound according to any of Examples 1 to 16. The dye solution contains 1% on mass of fibre of dye, 80g/L Na_2SO_4 and 5% on mass of fibre of sodium acetate. The cotton fabrics are soaked in water and then the cotton fabrics are dyed in the above dye-bath at pH 7 at 50°C for 15 minutes. The dyed cotton fabric is then fixed in the dye-bath at pH 11.5 with addition of 30g/L of trisodium phosphate and dyeing continued at 50°C for 45 minutes. The dyed fabric is rinsed with water.

In the above dyeing procedure the dye bath for each dye compound is almost totally exhausted (i.e. only slight colour in the dye bath after dyeing), indicating that the compounds prepared according to Examples 1 to 16 each have a high Exhaustion Value (typically >95%). The Exhaustion Values for each product can be obtained by comparing the photo-absorption of the dyebath liquid before and after dyeing. The Exhaustion Values for Examples 1 to 16 are given in Table A below.

Soaping-off process

A soaping off process can then be carried out by washing the dyed fabrics with an aqueous solution of Sandozine NIE (2g/L) (available from Clariant (Switzerland) Ltd., R&D Dyestuffs, Post Box, Building 88/1007, CH-4002 Basel) at 100°C for 30 minutes.

In the above soaping-off process hardly any colour was removed from the fabric, resulting in an almost colourless soaping liquid, indicating that the compounds prepared according to Examples 1 to 16 each have a high degree of dye -fibre covalent bonding and a high Fixation Value (typically >95%). The Fixation Values of the dye products prepared according to Examples 1 to 16 are shown in Table A below.

From the Exhaustion and Fixation Values, the Efficiency Values for each dye product can be calculated.

Table A - Exhaustion, Fixation and Efficiency Values for the dye products of Examples 1 to 16

Eg.	Exhaustion Value (E%)	Fixation Value (F%)	Efficiency Value (T)
1	97.32%	97.21%	94.61
2	98.90%	97.05%	95.98
3	97.27%	96.07%	93.45
4	98.68%	98.27%	96.98
5	98.71%	97.99%	96.72
6	98.71%	97.99%	96.72
7	97.62%	>95%	>90
8	97.62%	99.62%	97.24
9	98.19%	99.01%	97.21
10	99.12%	97.75%	96.88

11	96.51%	99.45%	95.98
12	98.28%	98.39%	96.98
13	98.90%	98.73%	97.64
14	97.95%	97.26%	95.27
15	99.62%	98.24%	97.86
16	97.72%	98.47%	96.25

The E, F and T values of the dyes according to the present invention are typically higher than many of the commercially available starting materials. In particular, the F and T values of the dyes according to the present invention are significantly higher than those of the commercially available starting materials.

Co3 (International Standards Organisation) Wash Fastness Test

The dyed fabrics are washed with an aqueous solution containing ECE Reference Detergent (5g/ml) and sodium carbonate (2g/ml) at 60°C for 30 minutes.

In the above wash fastness test, no noticeable colour was removed from the cotton fibre and no staining of the white adjacent fibres occurred (using Multiple Fibre adjacent strip supplied by the Society of Dyes and Colourists, Bradford, UK).

Example 20

All dye compounds prepared according to Examples 1 to 16 can be used to dye nylon or wool using the dyeing procedures detailed below. After the nylon/wool dyeing procedure has been carried out a wash-test procedure can be carried out on the dyed fabric to test the wash-fastness of the dye compounds.

Wool/Nylon Dyeing Procedure

The wool/nylon fabric is soaked in a 2% w/w Alcopol-O (40% w/w sodium-diisooctylsulpho- succinate commercially available from Allied Colloids) solution. The fabric is then dyed for 1 hour at 100°C and pH 3.5 in a dye-bath containing the following compositions: 1.2% on mass of fibre of dye prepared according to any of Examples 1 to

7, 5% on mass of fibre of sodium acetate, 1% Albegal B (commercially available from Ciba). The dyed wool/nylon fabric was then rinsed with water.

In the above procedure intense dyeings are provided for each of the compounds prepared according to Examples 1 to 16.

Co2 (ISO) Wash Fastness Test Procedure for Wool/Nylon Fabrics

The dyed wool/nylon fabric is washed in an aqueous solution containing 5g/L of ECE Reference Detergent (commercially available from the Society of Dyers and Colourists, Bradford, UK) at 50°C for 45 minutes.

In the above wash fastness test, no noticeable colour was removed from the wool fibre and no staining of the white adjacent fibres occurred ((using Multiple Fibre adjacent strip supplied by SDC Bradford)

Table A

Eg	Starting Dye	Sugar	x	y	z	a	b	c	d	e	Final Dye	f
1	Remazol Red RB	Glucose	4g	35-40°C	4-5	1.2g	<pH2	3-3.5hr	35-40°C	1-2hrs	Remazol Red RB/Glu	Deep Red
2	Remazol Yellow 3RS	Glucose	4g	30-35°C	3.5-4.5	1.2g	<pH2	2.5-3hr	30-55°C	1-1.5hrs	Remazol Yellow 3RS/Glu	Yellow
3	Remazol Turquoise Blue G	Glucose	4g	40-45°C	4-5	1.2g	<pH2	3-4hrs	40-45°C	1-1.5hrs	Remazol Turquoise Blue G/Glu	Turquoise Blue
4	Remazol Brill Blue R Special	Glucose	4g	35-40°C	4.5-5.5	1.2g	<pH2	3-3.5hrs	35-40°C	1-1.5hrs	Remazol Brill Blue R Special/Glu	Deep Blue
5	Cibacron Red C2G	Glucose	4g	25-30°C	4-4.5	1.2g	<pH2	3-4hrs	25-30°C	2-3hrs	Cibacron Red C2G/Glu	Deep Red
6	Cibacron Yellow C2R	Glucose	4g	30-35°C	4-4.5	1.2g	<pH2	3-3.5hrs	30-35°C	2-3hrs	Cibacron Yellow C2R/Glu	Yellow
7	Cibacron Blue CR	Glucose	4g	30-35°C	4-4.5	1.2g	<pH2	3-4hrs	30-35°C	2-3hrs	Cibacron Blue CR/Glu	Deep Blue
8	Sumifix	Glucose	4g	40-	4.2-4.8	1.2g	<pH2	3-4hrs	40-	2-3hrs	Sumifix Supra	Deep Red

	Supra Red 2BF			45°C						45°C			Red 2BF/Glu	
--	------------------	--	--	------	--	--	--	--	--	------	--	--	-------------	--

Table A												
Eg	Starting Dye	Sugar	X	Y	Z	A	B	C	D	E	Final Dye	F
9	Sumifix Supra Yellow 3RF	Glucose	4g	40-45°C	4-4.5	1.2g	<pH2	3-4hrs	40-45°C	2-3hrs	Sumifix Supra Yellow 3RF/Glu	Yellow
10	Sumifix Supra Blue BRF	Glucose	4g	40-45°C	4.2-4.8	1.2g	<pH2	3-4hrs	40-45°C	2-3hrs	Sumifix Supra Blue BRF/Glu	Blue
11	Sumifix Supra Turquoise BGF	Glucose	4g	40-45°C	3.5-4.2	1.2g	<pH2	3-4hrs	40-45°C	2-3hrs	Sumifix Supra Turquoise BGF/Glu	Turquoise
12	Remazol Red RB	Sucrose	4g	40-45°C	4.5-5.5	1g	pH2.5	3-4hrs	40-45°C	1-2hrs	Remazol Red RB/SG	Deep Red
13	Remazol Yellow 3RS	Sucrose	4g	40-45°C	4.5-5.5	1g	pH2.5	3-4hrs	40-45°C	1-1.5hrs	Remazol Yellow 3RS/SG	Yellow
14	Remazol Turquoise Blue G	Sucrose	4g	40-45°C	4-5	1g	pH2.5	4-5hrs	40-45°C	1-1.5hrs	Remazol Turquoise Blue G/SG	Deep Blue
15	Remazol Brill Blue R Special	Sucrose	4g	45-50°C	4-4.5	1g	pH2.5	4-5hrs	40-45°C	1-2hrs	Remazol Brill Blue R Special/SG	Deep Blue

16	Remazol RedRB	Formic Acid	4g	20-22°C	4.5-5.5	1g	pH3-3.5	3-4hrs	20-22°C	1-1.5hrs	Remazol Red RB/SG	Deep Red
----	------------------	----------------	----	---------	---------	----	---------	--------	---------	----------	----------------------	----------

Claims:

1. A reactive dye compound comprising:


- (a) at least one chromophore moiety;
- (b) at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore moiety either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group L;

characterised in that at least one $\text{SO}_2\text{C}_2\text{H}_4$ group is substituted on its terminal carbon atom with at least one Y group wherein Y is derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the $\text{SO}_2\text{C}_2\text{H}_4$ group thereby forming a hemiacetal.

- 2. A reactive dye compound according to Claim 1 wherein Y is derived from a hydrated aldehyde or ketone or the hydrated form of formic acid.
- 3. A reactive dye compound according to Claim 1 or 2 wherein Y is derived from the hydrated form of a reducing sugar selected from an aldose or a ketose, or the hydrated form of formic acid.
- 4. A reactive dye compound according to Claim 3 wherein said aldose is selected from an aldotriose, an aldotetrose, an aldopentose, an aldohexose, an aldohexose and an aldooctose, and mixtures thereof.
- 5. A reactive dye compound according to Claim 4 wherein said aldose is an aldopentose selected from ribose, xylose, arabinose, deoxyribose and fructose, and mixtures thereof.

6. A reactive dye compound according to Claim 5 wherein said aldose is an aldohexose selected from glucose, galactose, talose, mannose, altrose, allose and rhamnose, and mixtures thereof.
7. A reactive dye compound according to any of Claims 1 to 6 wherein Y is derived from glucose, sucrose or fructose or the hydrated form of formic acid.
8. A reactive dye compound according to Claim 3 wherein said ketose is selected from an aldotetrulose, an aldopentulose, an aldohexulose, an aldohexulose, and an aldooctulose, and mixtures thereof.
9. A reactive dye compound according to any of Claims 1 to 8 wherein Y is -O-(CHOH)₄(CHOHCH₂OH).
10. A reactive dye compound having the formula (I):
$$D-(L)_r-SO_2-CH_2CH_2-Y$$
wherein:
 - D is a chromophore group;
 - r is 0 or 1
 - L is a linking group selected from:

NH, $(\text{CH}_2)_n$, $\text{N}-(\text{CH}_2)_n\text{N}$, $-(\text{CH}_2)_n\text{N}$, NR (R is C1-C4 alkyl)



wherein Ar is an aryl group, preferably benzene, Y is as defined above, X is selected from thio-derivatives, halogen (preferably fluorine and chlorine), amines, alkoxy groups, carboxylic acid groups, CN, N_3 , quaternized nitrogen derivatives, Q^+ , and oxy- or thio- carbonyl


derivatives having the formula $-A(CO)R^*$ wherein A is selected from O or S, where R^* is an organic residue which contains at least one nucleophilic group, wherein the nucleophilic group is preferably selected from OH, NH_2 , SH, COOH, $-N=$, NHR^1 and NR^1R^2 wherein R^1 and R^2 may be the same or different and may be selected from C_1 - C_4 alkyl; Z is a nitrogen-containing heterocycle, n is an integer of from 1 to 4;

and salts thereof.

11. A reactive dye compound according to Claim 10 wherein Z is selected from triazine, pyrimidine, quinoxaline, pyrimidinone, phthalazine, pyridazone and pyrazine.


12. A reactive dye compound according to Claim 10 or 11 wherein r is 0.

13. A reactive dye compound having the structure:



wherein D, Z, and Y are as defined above.

14. A reactive dye compound having the structure:



wherein D, Y and Ar are as defined above.

15. Use of a compound according to any of Claims 1 to 14 for dyeing cellulosic substrates, preferably cotton.

16. Use of a compound according to any of Claims 1 to 14 for dyeing wool.
17. Use of a compound according to any of Claims 1 to 14 for dyeing polyamide substrates, preferably nylon.
18. Use of a compound according to any of Claims 1 to 14 for dyeing silk.
19. Use of a compound according to any of Claims 1 to 14 for dyeing keratin, preferably hair.
20. Use of a compound according to any of Claims 1 to 14 for dyeing leather.
21. Process for the preparation of a compound according to any of Claims 1 to 14 comprising the steps of reacting a first starting material with a second starting material, the first starting material comprising at least one chromophore and at least one $\text{SO}_2\text{C}_2\text{H}_4$ group which is attached to the chromophore group either directly via the sulphur atom of the $\text{SO}_2\text{C}_2\text{H}_4$ group or via a linking group, the second starting material being a compound containing a suitable Y group, preferably the hydrated form of a reducing sugar.
22. Process according to Claim 21 wherein the reducing sugar is selected from sucrose, glucose and mixtures thereof.
23. Process according to Claim 21 or 22 wherein the process is carried out at a pH of from about 2 to about 8.
24. Process according to any of Claims 21 to 23 wherein the second starting material is added to the first starting material slowly, preferably dropwise, preferably over several hours, preferably 1 to 5 hours, more preferably 1 to 3 hours.
25. Product obtainable by the process according to any of Claims 21 to 24.

26. A dye composition comprising the compound of any of Claims 1 to 14 or the product of any of Claims 21 to 25.
27. A dye composition according to Claim 26 wherein the composition is in the form of a solid mixture and further comprises an acidic or neutral buffer.
28. A dye composition according to Claim 26 wherein the composition is in the form of a liquid and further comprises water and an acidic or neutral buffer.
29. A dye composition according to Claim 26 wherein the composition is in the form of a paste and further comprises water, thickening agent and an acidic or neutral buffer.
30. A dye composition according to any of Claims 26, 28 or 29 wherein the pH of the composition is in the range of from about 2 to about 5, preferably from about 2 to about 3 when an acidic buffer is present, and in the range of from about 4 to about 8, preferably from about 6 to about 8 when a neutral buffer is present.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 April 2001 (12.04.2001)

PCT

(10) International Publication Number
WO 01/25338 A1

(51) International Patent Classification⁷: **C09B 62/78**,
D06P 3/00, 1/38, C09B 62/503, 62/44

(GB). YOUSAF, Taher, Iqbal [GB/GB]; 10 School Lane,
Egham, Surrey TW20 9LQ (GB).

(21) International Application Number: PCT/US00/26975

(74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).

(22) International Filing Date:
29 September 2000 (29.09.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
9923328.0 1 October 1999 (01.10.1999) GB
0006969.0 22 March 2000 (22.03.2000) GB
0009842.6 25 April 2000 (25.04.2000) GB

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(71) Applicant (*for all designated States except US*): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): BROADBENT, Peter, Jeffrey [GB/GB]; 33 Whincup Avenue, Knaresborough, North Yorkshire HG5 0JH (GB). LEWIS, David, Malcolm [GB/GB]; 13 St. Richards Road, Otley, West Yorkshire LS21 2AL (GB). GENAIN, Gilles, Yves, Marie, Fernand [FR/GB]; 7 Stamford Brook Avenue, London W6 0YB (GB). HE, Wei, Dong [GB/GB]; 11 Tingley Common, Morley, Leeds, Yorkshire LS27 0HF

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: REACTIVE DYE COMPOUNDS

(57) Abstract: A reactive dye compound comprising (a) at least one chromophore moiety; (b) at least one SO₂C₂H₄ group which is attached to the chromophore moiety either directly via the sulphur atom of the SO₂C₂H₄ group or via a linking group L; characterised in that at least one SO₂C₂H₄ group is substituted on its terminal carbon atom with at least one Y group wherein Y is derived from a hydrated aldehyde, a hydrated ketone, a hydrated alpha-hydroxy ketone or the hydrated form of formic acid, and linked via one of its oxygen atoms to the terminal carbon of the SO₂C₂H₄ group thereby forming a hemiacetal. The compounds herein have high Exhaustion Values (E), high Fixation Values (F) and high Efficiency Values (T) and show significant improvements in terms of reducing spent dyestuff in effluent, increasing dye affinity to the substrate, increasing the dye-substrate covalent bonding, increasing the ability to dye substrates at room temperature, decreasing the amount of dye that is removed during the post dyeing "soaping off process" and therefore simplifying the post dyeing "soaping off process" traditionally associated with dyeing cotton with fibre reactive dyes and reduction of staining of adjacent white fabrics. In addition, the compounds prepared above provide more intense dyeings and require less levels of salt for dyeing cotton substrates.

WO 01/25338 A1

DECLARATION COMBINED WITH POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

"Reactive Dye Compounds"

bearing the above listed Procter & Gamble Company Case number, the specification of which was filed as PCT/US00/26975, designating at least the United States of America, with the United States Receiving Office on 29 September 2000.

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37 Code of Federal Regulations §1.56.

I hereby claim foreign priority benefits under Title 35 United States Code §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

PRIOR FOREIGN APPLICATION(S) TO WHICH WE CLAIM PRIORITY:

9923328.0	GB	01 October 1999
0006969.0	GB	22 March 2000
0009842.6	GB	25 April 2000

I hereby claim the benefit under Title 35 United States Code §120 of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35 United States Code §112, I acknowledge the duty to disclose material information as defined in Title 37 Code of Federal Regulations §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

Appln. Serial No.	Filing Date	Status - patented, pending, abandoned
Appln. Serial No.	Filing Date	Status - patented, pending, abandoned

I hereby appoint the following as my attorney(s) or agent(s) with full power of substitution to prosecute this application and transact all business in the Patent and Trademark office connected therewith:

Name	Registration No.	Associate Power of Attorney Attached [] Yes [] No
Jacobus C. Rasser	37,043	
T. David Reed	32,931	
Eileen L. Hughett	34,352	
Timothy B. Guffey	41,048	
Emelyn L. Hiland	41,501	

SEND CORRESPONDENCE TO:

T. David Reed, c/o The Procter Gamble Company (513) 627-7025

Name	Phone No.
5299 Spring Grove Avenue Cincinnati Ohio	45217-1087
Street City State	Zip Code

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor: ¹⁻⁰⁰ BROADBENT, Peter Jeffrey

Inventor's signature Peter Jeffrey Broadbent Date 15 January 2001

Residence: 33 Whincup Avenue, Knaresborough North Yorkshire, HG5 0JH GB

Citizenship: GB DEX

Post Office Address: 5299 Spring Grove Ave., Cincinnati, Ohio 45217-1087

Full name of second joint inventor, if any: ²⁻⁰⁰ LEWIS, David Malcolm

Inventor's signature David Malcolm Lewis Date 21 Dec 2000

Residence: 13 St. Richards Road, Otley West Yorkshire LS21 2AL GB

Citizenship: GB DEX

Post Office Address: 5299 Spring Grove Ave., Cincinnati, Ohio 45217-1087

Full name of third joint inventor, if any: ³⁻⁰⁰ GENAIN, Gilles Yves Marie Fernand

Inventor's signature Genain Gilles Yves Marie Fernand Date 14-11-2000

Residence: 7 Stamford Brook Avenue London W6 0YB GB

Citizenship: FR FRX

Post Office Address: 5299 Spring Grove Ave., Cincinnati, Ohio 45217-1087

Full name of fourth joint inventor, if any: ⁴⁻⁰⁰ HE, Wei Dong

Inventor's signature Wei Dong He Date 10/1/01

Residence: 11 Tingley Common, Morley Leeds, Yorkshire, LS27 0HF GB

Citizenship: GB DEX

Post Office Address: 5299 Spring Grove Ave., Cincinnati, Ohio 45217-1087

5-00
Full name of fifth joint inventor, if any: YOUSAF, Taher Iqbal
Inventor's signature Taher Iqbal Yousaf Date 24.11.00
Residence: 10 School Lane Egham, Surrey TW20 9LQ GB
Citizenship: GB DEX
Post Office Address: 5299 Spring Grove Ave., Cincinnati, Ohio 45217-1087
